Product Data sheet

22 June 2019 Rev 2

SEJI CHEMICAL CO,. LTD.

SJ-505ESTR

Crosslinkable Semiconductive Shielding Compound

Overview

SJ-505ESTR is a specially formulated crosslinkable semiconductive polyethylene copolymer compound for strippable insulation shielding of medium voltage XLPE insulated power cable. (up to 46 kV)

SJ-505ESTR is specifically developed to provide a super-smooth surface yielding virtually perfect interface between the extruded shield and insulation.

SJ-505ESTR has stable volume resistivity characteristics at elevated temperatures and excellent tree retardant properties.

Specifications

ICEA S-93-639, ICEA S-94-649
IEC 60502-2
AEIC CS8
UL 1072

Properties

This TDS is typical data only and are not to be construed as specifications. Users should results their own test. Tests are conducted on compression molded slabs cured 15 minutes at 180℃.

Physical	**Value (English)**	**Value (SI)**	**Test Method**
Density	1.16 g/㎤	1.16 g/㎤	ASTM D 1505
Moisture Content	300 ppm	300 ppm	ASTM D 6869
Melt Flow Rate[125°C(257°F)/10.0 kg]	2.00 g/10min	2.00 g/10min	ASTM D 1238
Stripping Force[250mm/min, width 10mm, 23°C(73°F) 180angle]	8.57 lbs/in	1.50 kN/m	ASTM D 903
Brittleness temperature	<-40 °C	<-40 °C	ASTM D 746
Metal ion content	<500 ppm	<500 ppm	

Mechanical	**Value (English)**	**Value (SI)**	**Test Method**
Ultimate Tensile Strength	2321 psi	16.0 Mpa	ASTM D 638
Elongation at Break	305 %	305 %	ASTM D 638
Retention of Tensile Strength After Ageing - 135°C[275°F], 168hrs	95 %	95 %	ASTM D 638
Retention of Elongation After Ageing - 135°C[275°F], 168hrs	93 %	93 %	ASTM D 638

Electrical	**Value (English)**	**Value (SI)**	**Test Method**
Volume Resistivity			ASTM D 991
at 23℃[73.4℉]	300 Ωcm	300 Ωcm	
at 90℃[194°F]	1,000 Ωcm	1,000 Ωcm	
at 135℃[275°F]	1,000 Ωcm	1,000 Ωcm	

Processing

SJ-505ESTR provides excellent surface finish and outstanding output rates over a broad range of extrusion a broad range of extrusion conditions.

Head office, Plant1 : 72 Daedeok-ro, Eumseong-gun, Chungcheongbuk-do,Korea[27649]
Plant2 : 349-24 Geumyul-ro, Eumseong-gun, Chungcheongbuk-do, Korea[27648]
Telephone. +82-43-881-1999 Fax. +82-43-882-0183 W. www.sjccom.com

Product Data sheet

22 June 2019 Rev 2

SEJI CHEMICAL CO,. LTD.

SJ-505ESTR

Crosslinkable Semiconductive Shielding Compound

SJ-505ESTR requires melt stock temperatures in the range of 110℃ to 120℃ for best results. Lower melt temperatures may result in a unmelt extrudate and higher melt temperatures may result in extrudate scorch and It can even trigger die-drools.
The curing configuration the maximum cable surface temperature in the curing zone should be maintained below 200ºC (392 ºF). If the surface temperature of the cable in the curing zone is over 200ºC, it may cause cracks in the cable, so careful temperature control required. Dehumidified hopper drying at 25~40℃ for up to 4 hours prior to extrusion might be employed to remove moisture. Specific processing conditions depend on equipment and cable dimensions.
Optimum conditions by conventional practices should be established.

Packing & Storage

Packed in 600kg polybag lined carton box.
Recommended maximum storage period is 12months unopened and in original packaging after the manufacture.

Stored at room temperatures 73 ℉ 23 ℃
The shelf life of this product is 1 year from the date of manufacture.

Safety

Please contact Seji Chemical for Material Safety Data Sheet.

Disclaimer

Information contained in this data sheet is up-to-date and correct as at the date of issue.
Seji chemical Co., Ltd. cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use.
Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. **Therefore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal binding effect.**
To the maximum extent permitted by law, **Seji chemical Co., Ltd.** will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet.
No express or implied warranties are given other than those implications mandatory by law.

Head office, Plant1 : 72 Daedeok-ro, Eumseong-gun, Chungcheongbuk-do,Korea[27649]
Plant2 : 349-24 Geumyul-ro, Eumseong-gun, Chungcheongbuk-do, Korea[27648]
Telephone. +82-43-881-1999 Fax. +82-43-882-0183 W. www.sjccom.com